



17025 SO. MAIN ST. GARDENA, CA 90248 | 800.572.9029  
13238 SO. FIGUEROA ST. LOS ANGELES, CA 90061 | stepstoneprecast.com

## MATERIAL PRODUCT DATA SHEET

### Product Name

Classic Garden Step

### Manufacturer

Stepstone, LLC  
17025 So. Main St.  
Gardena, CA 90248

Phone 310-327-7474  
Fax 310-217-1424  
Toll Free 800-572-9029

### Product Description

Stepstone has produced high quality precast concrete since 1963. Classic Garden Steps provide distinctive good looks with high strength hardrock concrete. The Classic Garden Step has a 2" bullnose edge with a ¼" top and bottom reveal. They work well as a design element to refine any project. The system includes straights, corners and inside and outside radius components. The Classic Garden Step is designed to be used for both commercial and residential applications.

### Composition & Materials

Classic Garden Steps are hand-made, wet-cast from 4000 PSI hardrock concrete, using Type III cement.

### Sizes

Classic Garden Step straights are 14"x24"x2-1/2"; corners are 14"x16"x2-1/2"; radius components vary.

### Finishes

Classic Garden Step available finishes include: fine grain stipple, and light, medium or heavy sandblast.

### Colors

Classic Garden Steps are available in 12 standard colors: Adobe, Agave, Almond, Brick Red, Cafe Brown, Caramel, French Gray, Granada White, Iceberg Green, Kona, Pebble and Porcelain; custom colors are available upon request.

### Technical Data

APPLICABLE STANDARDS: American Society for Testing & Materials (ASTM)

ASTM C33 - *Standard Specification for Concrete Aggregates*

ASTM C39 - *Concrete Compressive Strength*

ASTM C150 - *Standard Specification for Portland Cement*

ASTM C642 - *Water Absorption, Density, Voids in Hardened Concrete*

ASTM C666 - *Rapid Freeze/Thaw Resistance of Concrete*

ASTM C979 - *Pigments for Integrally Colored Concrete*

ASTM E303 - *Pendulum Slip Resistance*

### Physical / Chemical Properties

Classic Garden Steps is 28 LBS per square foot. Water absorption: Not more than 6.0 % average, not more than 7.0 % for any individual unit for standard colors. Unit length, width and height are not more than +/- 1/8" from standard dimensions. No unit will differ more than +/- 1/8" from the approved samples. Test reports are available upon request. Concrete is non-combustible.

*Please contact Stepstone, LLC for further information*

February 2025