

17025 SO. MAIN ST. GARDENA, CA 90248 800.572.9029 13238 SO. FIGUEROA ST. LOS ANGELES, CA 90061 stepstoneprecast.com

## **MATERIAL PRODUCT DATA SHEET**

**Product Name** 

**Hexagonal Paver** 

# Manufacturer

Stepstone, LLC 17025 So. Main St. Gardena, CA 90248 
 Phone
 310-327-7474

 Fax
 310-217-1424

 Toll free
 800-572-9029

## **Product Description**

Stepstone has produced high quality precast concrete since 1963. Hexagonal Pavers are precast concrete pavers that come in many standard sizes. Hexagonal Pavers are designed to be used for both commercial and residential applications.

## **Composition & Materials**

Hexagonal Pavers are hand-made, wet-cast from 5000 PSI hard rock concrete using Type III cement.

### Sizes

Hexagonal Pavers are available in standard sizes. 16''x 2'' thickness,  $20 \frac{1}{2}''$  and  $24'' x 2 \frac{1}{2}''$  thickness. Corner and Starter pieces also available. See Hexagonal Paver details for more size information.

### Finishes

Hexagonal Pavers available finishes include: light, medium or heavy sandblast

## Colors

Hexagonal Pavers are available in 12 standard colors: Adobe, Agave, Almond, Brick Red, Cafe Brown, Caramel, French Gray, Granada White, Iceberg Green, Kona, Pebble and Porcelain; custom colors are available upon request.

## **Technical Data**

APPLICABLE STANDARDS: American Society for Testing & Materials (ASTM) ASTM C33 - Standard Specification for Concrete Aggregates ASTM C39 - Concrete Compressive Strength ASTM C150 - Standard Specification for Portland Cement ASTM C642 - Water Absorption, Density, Voids in Hardened Concrete ASTM C666 - Rapid Freeze/Thaw Resistance of Concrete ASTM C979 - Pigments for Integrally Colored Concrete ASTM E303 - Pendulum Slip Resistance

#### **Physical /Chemical Properties**

Hexagonal Paver weight is 22-28 LBS per square foot. Water absorption: Not more than 6.0 % average, not more than 7.0 % for any individual unit for standard colors. Unit length, width and height are not more than +/-1/8'' from standard dimensions. No unit will differ more than +/-1/8'' from the approved samples. Test reports are available upon request. Concrete is non-combustible.