17025 SO. MAIN ST. GARDENA, CA 90248 800.572.9029
13238 SO. FIGUEROA ST. LOS ANGELES, CA 90061 stepstoneprecast.com

## **MATERIAL PRODUCT DATA SHEET**

# **Product Name**

Modern Pool Coping

# Manufacturer

 Stepstone, LLC
 Phone
 310-327-7474

 17025 So. Main St.
 Fax
 310-217-1424

 Gardena, CA 90248
 Toll Free
 800-572-9029

# **Product Description**

Stepstone has produced high quality precast concrete since 1963. Modern Pool Coping provides distinctive good looks with high strength hardrock concrete. The Modern Pool Coping has a rolling 2" bullnose edge. They work well as a design element to refine any project. The system includes straights and corners. They are designed to be used for both commercial and residential applications.

# **Composition & Materials**

Modern Pool Copings are hand-made, wet-cast from 4000 PSI hardrock concrete, using Type III cement.

#### Sizes

Modern Pool Coping straights are 18"x24"x2" and 18"x18"x2"; corners are 18"x18"x2".

## **Finishes**

Modern Pool Coping available finishes include: fine grain stipple, and light, medium or heavy sandblast

## Colors

Modern Pool Copings are available in 12 standard colors: Adobe, Agave, Almond, Brick Red, Cafe Brown, Caramel, French Gray, Granada White, Iceberg Green, Kona, Pebble and Porcelain; custom colors are available upon request.

# **Technical Data**

APPLICABLE STANDARDS: American Society for Testing & Materials (ASTM)

ASTM C33 - Standard Specification for Concrete Aggregates

ASTM C39 - Concrete Compressive Strength

ASTM C150 - Standard Specification for Portland Cement

ASTM C642 - Water Absorption, Density, Voids in Hardened Concrete

ASTM C666 - Rapid Freeze/Thaw Resistance of Concrete

ASTM C979 - Pigments for Integrally Colored Concrete

ASTM E303 - Pendulum Slip Resistance

# **Physical / Chemical Properties**

Modern Pool Coping weight is 22 LBS per square foot. Water absorption: Not more than 6.0% average, not more than 7.0% for any individual unit for standard colors. Unit length, width and height are not more than +/-1/8" from standard dimensions. No unit will differ more than +/-1/8" from the approved samples. Test reports are available upon request. Concrete is non-combustible.